



A woven geotextile fabric, produced from high-tenacity polypropylene slit-film. This high-modulus fabric is ideally suited for light-weight separation / stabilization applications. GTF 270 has been UV stabilized and packaged in conformance with ASTM D4873.

<i>PROPERTY</i>	<i>TEST PROCEDURE</i>	<i>METRIC</i>		<i>ENGLISH</i>	
		MARV		MARV	
Grab Tensile Strength (W/F)	ASTM D-4632	1201	N	270	lbs
Grab Elongation	ASTM D-4632	20/15	%	20/15	%
Trapezoid Tear	ASTM D-4533	445	N	100	lbs
Puncture	ASTM D-4833	534	N	120	lbs
CBR puncture	ASTM D-6241	4116	N	925	lbs
Mullen Burst	ASTM D-3786	4137	KPa	600	psi
Permittivity	ASTM D-4491	0.050	sec ⁻¹	0.050	sec ⁻¹
A.O.S.	ASTM D-4751	0.425	mm	40	U.S. Sieve
UV Resistance (500 hrs)	ASTM D-4355	80	%	80	%
Water Flow Rate	ASTM D-4491	163	lpm/m ²	4	gpm/ft ²

<i>VOLUME</i>	<i>TEST PROCEDURE</i>	<i>METRIC</i>		<i>ENGLISH</i>	
		Typical		Typical	
Weight	ASTM D-5261	200	g/m ²	5.9	oz/yd ²
Thickness	ASTM D-5199	.660	mm	26	mils

<i>PACKAGING</i>	<i>METRIC</i>			<i>ENGLISH</i>		
	AREA	WIDTH	LENGTH	AREA	WIDTH	LENGTH
Roll sizes	501 m ²	3.81 m	131.6 m	600 yd ²	12.5'	432'
	501 m ²	4.57 m	91.4 m	600 yd ²	15'	300'
	501 m ²	5.33 m	94.1 m	600 yd ²	17.5'	309'
	669 m ²	3.81 m	175.5 m	800 yd ²	12.5'	576'
	669 m ²	4.57 m	146.2 m	800 yd ²	15'	480'
	669 m ²	5.33 m	125.2 m	800 yd ²	17.5'	411'

This information relates to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date compiled. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself or herself as to the suitability and completeness of such information for his or her own particular use. We do not accept liability for any loss or damage that may occur from the use of this information, nor do we offer any warranty against infringement.

LINQ and the Thrace-LINQ emblem are registered trademarks of Thrace-LINQ, Inc.